

Version: TE103/01

Tectyl™ Underbody Coating Bronze

Premium general purpose, corrosion preventive compound.

Tectyl Underbody Coating Bronze is a solvent cutback wax/asphaltic base, corrosion preventive. It is especially suitable to be applied to the underbody of vehicles.

Tectyl Underbody Coating Bronze cures to a bronze colored, resilient, tough and abrasive resistant film.

Approvals/Performance levels

Tectyl Underbody Coating Bronze

Accelerated Corrosion tests:
@ Average recommended DFT

Accelerated Corrosion tests:
Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS
(Q-Panels, Type R, ASTM A1008)
40+ days

Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH
(Q-Panels, Type R, ASTM A1008)
100+ days

Applications

Surface Preparation:

The maximum performance of **Tectyl Underbody Coating Bronze** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Avoid direct contact of the product with PVC due to possible material incompatibility.

Application:

Tectyl Underbody Coating Bronze is formulated to be used as supplied. It is recommended that the ambient and product temperature should be between 10-35 °C at the time of product application. Shake the can well before use and spray at a distance of approximately 30 cm from the surface.

Removal:

Tectyl Underbody Coating Bronze can be removed with mineral spirits or any similar petroleum solvent, vapor degreasing, hot alkaline wash or low-pressure steam. Also, Tectyl Biocleaner can be used to remove Tectyl Underbody Coating Bronze.

Features & Benefits

Superior Protection

At the recommended DFT, the water resistance and displacement provide extraordinary protection against stone chipping and corrosion.

Multi-functional

Tectyl Underbody Coating can be applied on many different vehicles, such as cars, trucks, busses, campers, but also trailers and caravans.

Processing

Tectyl Underbody Coating Bronze is an easy to apply, elastic, protective underbody coating.

Multiple substrates

The underbody coating can also be used on different substrates, such as the wooden underside of a campers or caravans.

Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyleurope.com

Typical properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl Underbody Coating Bronze	
Flash Point, PMCC [°C]	<0
Nature of propellant	Propane /Butane
Recommended Dry Film Thickness over metal profile [microns]	250
Recommended Dry Film Thickness	Can only be reached by multiple spraying
Volatile Organic Compound Content of Concentrate ISO 11890-2 (10.4) [g/ltr]	593

This information only applies to products manufactured in the following location(s): Europe

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet <http://sds.valvoline.com>

Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

Storage

Tectyl Underbody Coating Bronze should be stored at temperatures between 10-35 °C. Shake well before use! Under proper storage conditions Tectyl Underbody Coating Bronze is best before 36 months after production date.

Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT OR TORCHES. Refer to The Safety Data Sheet for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Typical Properties section. If a primer, other than a Valvoline recommended product is required, written authorization must be obtained from Valvoline.

Replaces –

™ Trademark of Valvoline, registered in various countries © 2019

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ellis Enterprises B.V. and its affiliates assume legal responsibility.